



## EasyWeed®, EasyWeed® Electric, EasyWeed® Glow in the Dark

For Use On: 100% Cotton | Poly/cotton blends | 100% Polyester | Leather



### Application Instructions (Home Iron):

- Set iron dial between Cotton and Linen.
- Cover design with Heat Transfer Cover Sheet or Multipurpose Paper.
- Place on flat, hard surface (ironing board not recommended).
- Press iron with medium/firm pressure for 10-15 seconds.
- Peel carrier hot or cold.

### Application Instructions (Heat Press):

- Preheat garment for 2-3 seconds.
- Apply design at 305°F / 150°C (EasyPress® users add approx. 30°).
- Use medium pressure for 10-15 seconds.
- Peel carrier hot or cold.

### Laundrying:

- Wait 24 hours before first wash.
- Machine wash warm or cold with mild detergent.
- Do not bleach, dry clean, or use liquid fabric softener.
- Dry on normal dryer setting.

## EasyWeed® EcoStretch™

For Use On: 100% Cotton | Poly/cotton blends | 100% Polyester | Lycra®/Spandex



### Application Instructions (Home Iron):

- Set iron dial on Cotton.
- Cover design with Heat Transfer Cover Sheet or Multipurpose Paper.
- Place on flat, hard surface (ironing board not recommended).
- Press iron with medium pressure for 10-15 seconds.
- Peel carrier hot.

### Application Instructions (Heat Press):

- Preheat garment for 2-3 seconds.
- Apply design at 250°F / 120°C (EasyPress users add approx. 30°).
- Use medium pressure for 10-15 seconds.
- Peel carrier hot.

### Laundrying:

- Wait 24 hours before first wash.
- Machine wash cold with mild detergent.
- Do not bleach, dry clean, or use liquid fabric softener.
- Dry on low dryer setting.

## EasyWeed® Extra

For Use On: 100% Cotton | Poly/cotton blends | 100% Polyester | Nylon



### Application Instructions (Home Iron):

- Set iron dial between Cotton and Linen.
- Cover design with Heat Transfer Cover Sheet or Multipurpose Paper.
- Place on flat, hard surface (ironing board not recommended).
- Press iron with medium/firm pressure for 10-15 seconds.
- Peel carrier hot or cold.

### Application Instructions (Heat Press):

- Preheat garment for 2-3 seconds.
- Apply design at 305°F / 150°C (EasyPress users add approx. 30°).
- Use medium pressure for 10-15 seconds.
- Peel carrier hot or cold.

### Laundrying:

- Wait 24 hours before first wash.
- Machine wash cold with mild detergent.
- Do not bleach, dry clean, or use liquid fabric softener.
- Dry on low dryer setting.
- Wash inside out for best results.

## EasyWeed® Stretch

For Use On: 100% Cotton | Poly/cotton blends | 100% Polyester | Nylon



### Application Instructions (Home Iron):

- Set iron dial between Cotton and Linen.
- Cover design with Heat Transfer Cover Sheet or Multipurpose Paper.
- Place on flat, hard surface (ironing board not recommended).
- Press iron with firm pressure for 20 seconds.
- Peel carrier hot or cold.

### Application Instructions (Heat Press):

- Preheat garment for 2-3 seconds.
- Apply design at 320°F / 160°C (EasyPress users add approx. 30°).
- Use firm pressure for 20 seconds.
- Peel carrier hot or cold.

### Laundrying:

- Wait 24 hours before first wash.
- Machine wash cold with mild detergent.
- Do not bleach, dry clean, or use liquid fabric softener.
- Dry on low dryer setting.
- Wash inside out for best results.

### RECOMMENDED ACCESSORIES:

Siser® EasyWeeder®, parchment or multipurpose paper, or heat transfer cover sheet.

If areas lift after application, cover and press for 5-10 seconds.

Due to variances in the manufacturing process of fabrics, Siser highly recommends testing prior to production.



## EasyWeed® Sub Block

For Use On: 100% Cotton | Poly/cotton blends | 100% Polyester | Leather



### Application Instructions (Home Iron):

- Set iron dial between Cotton and Linen.
- Cover design with Heat Transfer Cover Sheet or Multipurpose Paper.
- Place on flat, hard surface (ironing board not recommended.)
- Press iron with medium/firm pressure for 10-15 seconds.
- Peel carrier hot or cold.

### Application Instructions (Heat Press):

- Preheat garment for 2-3 seconds.
- Apply design at 265°F / 130°C (*EasyPress* users add approx. 30°).
- Use medium pressure for 10-15 seconds.
- Peel carrier hot or cold.

### Laundering:

- Wait 24 hours before first wash.
- Machine wash warm or cold with mild detergent.
- Do not bleach, dry clean, or use liquid fabric softener.
- Hang item to dry.

## EasyWeed® Adhesive

For Use On: 100% Cotton | Poly/cotton blends | 100% Polyester



### Application Instructions (Home Iron):

- Set iron dial between Cotton and Linen.
- Cover design with Heat Transfer Cover Sheet or Multipurpose Paper.
- Place on flat, hard surface (ironing board not recommended).
- Press iron with medium/firm pressure for 10-15 seconds.
- Peel carrier hot.

### Application Instructions (Heat Press):

- Preheat garment for 2-3 seconds.
- Apply design at 275°F / 135°C (*EasyPress* users add approx. 30°).
- Use medium pressure for 10-15 seconds.
- Peel carrier hot then apply top layer.

### Laundering:

- Wait 24 hours before first wash.
- Machine wash warm or cold with mild detergent.
- Do not bleach, dry clean, or use liquid fabric softener.
- Dry on normal dryer setting.

## EasyPatterns® Plus

For Use On: 100% Cotton | Poly/cotton blends | 100% Polyester



### Application Instructions (Home Iron):

- Set iron dial between Cotton and Linen.
- Cover design with Heat Transfer Cover Sheet or Multipurpose Paper.
- Place on flat, hard surface (ironing board not recommended).
- Press iron with medium/firm pressure for 15 seconds.
- Peel carrier hot or cold.

### Application Instructions (Heat Press):

- Preheat garment for 2-3 seconds.
- Apply design at 305°F / 105°C (*EasyPress* users add approx. 30°).
- Use medium pressure for 10-15 seconds.
- Peel carrier hot or cold.

### Laundering:

- Wait 24 hours before first wash.
- Machine wash warm or cold with mild detergent.
- Do not bleach, dry clean, or use liquid fabric softener.
- Dry on normal dryer setting.

## EasyReflective®

For Use On: 100% Cotton | Poly/cotton blends | 100% Polyester | Leather | Lycra®/Spandex



### Application Instructions (Home Iron):

- Set iron dial between Cotton and Linen.
- Cover design with Heat Transfer Cover Sheet or Multipurpose Paper.
- Place on flat, hard surface (ironing board not recommended).
- Press iron with medium/firm pressure for 10-15 seconds.
- Peel carrier warm.

### Application Instructions (Heat Press):

- Preheat garment for 2-3 seconds.
- Apply design at 305°F / 105°C (*EasyPress* users add approx. 30°).
- Use medium pressure for 15 seconds.
- Peel carrier warm (wait at least 15 seconds off press).

### Laundering:

- Wait 24 hours before first wash.
- Machine wash warm or cold with mild detergent.
- Do not bleach, dry clean, or use liquid fabric softener.
- Dry on normal dryer setting.

### RECOMMENDED ACCESSORIES:

Siser® EasyWeeder®, parchment or multipurpose paper, or heat transfer cover sheet.

If areas lift after application, cover and press for 5-10 seconds.

Due to variances in the manufacturing process of fabrics, Siser highly recommends testing prior to production.



## Easy® Glow

For Use On: 100% Cotton | Poly/cotton blends | 100% Polyester



### Application Instructions (Home Iron):

- Set iron dial between Cotton and Linen.
- Cover design with Heat Transfer Cover Sheet or Multipurpose Paper.
- Place on flat, hard surface (ironing board not recommended).
- Press iron with medium pressure 15 seconds.
- Peel carrier warm or cold.

### Application Instructions (Heat Press):

- Preheat garment for 2-3 seconds.
- Apply design at 305°F / 105°C (*EasyPress* users add approx. 30°).
- Use medium pressure for 15 seconds.
- Peel carrier warm or cold (5-10 seconds off press).

### Laundering:

- Wait 24 hours before first wash.
- Machine wash cold with mild detergent.
- Do not bleach, dry clean, or use liquid fabric softener.
- Dry on low dryer setting.

## Easy® Puff

For Use On: 100% Cotton | Poly/cotton blends | 100% Polyester

*Easy Puff is not recommended for use with a home iron.*



### IMPORTANT APPLICATION NOTES:

Easy® Puff is designed to withstand only one heat application. Repeated applications will “flatten” the puff effect permanently. It is recommended to apply *Easy Puff* last when used with other materials. It is not recommended for use with a home iron.

### Application Instructions (Heat Press):

- Preheat garment for 2-3 seconds.
- Apply design at 280°F / 138°C (*EasyPress* users add approx. 30°).
- Use medium pressure for 8-10 seconds.
- Peel carrier hot.

### Laundering:

- Wait 24 hours before first wash.
- Machine wash cold with mild detergent.
- Do not bleach, dry clean, or use liquid fabric softener.
- Dry on low dryer setting.
- Wash inside out for best results.

## Easy® Puff Metallic

For Use On: 100% Cotton | Poly/cotton blends | 100% Polyester

*Easy Puff is not recommended for use with a home iron.*



### IMPORTANT APPLICATION NOTES:

Easy® Puff Metallic requires two, 10-second presses. Layering and use of a home iron are not recommended with *Easy Puff Metallic*. It is recommended to apply *Easy Puff* last when used with other materials.

### Application Instructions (Heat Press):

- Preheat garment for 2-3 seconds.
- Apply design at 280°F / 138°C
- Use medium pressure for 10 seconds.
- Peel carrier hot.
- Cover and press for 10 seconds.

### Laundering:

- Wait 24 hours before first wash.
- Machine wash cold with mild detergent.
- Do not bleach, dry clean, or use liquid fabric softener.
- Dry on low dryer setting.
- Wash inside out for best results.

## Aurora™

For Use On: 100% Cotton | Poly/cotton blends | 100% Polyester



### Application Instructions (Home Iron):

- Set iron dial between Cotton and Linen.
- Cover design with Heat Transfer Cover Sheet or Multipurpose Paper.
- Place on flat, hard surface (ironing board not recommended).
- Press iron with medium/firm pressure for 15 seconds.
- Peel carrier completely cold.

### Application Instructions (Heat Press):

- Preheat garment for 2-3 seconds.
- Apply design at 305°F / 150°C (*EasyPress* users add approx. 30°).
- Use medium pressure for 15 seconds.
- Peel carrier completely cold.

### Laundering:

- Wait 24 hours before first wash.
- Machine wash cold with mild detergent.
- Do not bleach, dry clean, or use liquid fabric softener.
- Dry on low dryer setting.

### RECOMMENDED ACCESSORIES:

**Siser® EasyWeeder®, parchment or multipurpose paper, or heat transfer cover sheet.**

**If areas lift after application, cover and press for 5-10 seconds.**

**Due to variances in the manufacturing process of fabrics, Siser highly recommends testing prior to production.**



## BlackBoard®

For Use On: 100% Cotton | Poly/cotton blends | 100% Polyester



### Application Instructions (Home Iron):

- Set iron dial between Cotton and Linen.
- Cover design with Heat Transfer Cover Sheet or Multipurpose Paper.
- Place on flat, hard surface (ironing board not recommended).
- Press iron with medium/firm pressure for 10-15 seconds.
- Peel carrier warm.

### Application Instructions (Heat Press):

- Cut in reverse and weed excess material.
- Preheat garment for 2-3 seconds.
- Apply design at 275°F / 135°C (*EasyPress* users add approx. 30°).
- Use medium pressure for 15 seconds.
- Peel carrier warm.

### Laundrying:

- Wait 24 hours before first wash.
- Machine wash cold with mild detergent.
- Do not bleach, dry clean, or use liquid fabric softener.
- Dry on normal dryer setting.

## Brick® 600

For Use On: 100% Cotton | Poly/cotton blends | 100% Polyester



### Application Instructions (Home Iron):

- Set iron dial between Cotton and Linen.
- Cover design with Heat Transfer Cover Sheet or Multipurpose Paper.
- Place on flat, hard surface (ironing board not recommended).
- Press iron with medium/firm pressure for 20 seconds.
- Peel carrier cold.

### Application Instructions (Heat Press):

- Preheat garment for 2-3 seconds.
- Apply design at 310°F / 155°C (*EasyPress* users add approx. 30°).
- Use medium pressure for 20 seconds.
- Peel carrier cold.

### Laundrying:

- Wait 24 hours before first wash.
- Machine wash cold with mild detergent.
- Do not bleach, dry clean, or use liquid fabric softener.
- Dry on normal dryer setting.

## Glitter

For Use On: 100% Cotton | Poly/cotton blends | 100% Polyester | Leather



### Application Instructions (Home Iron):

- Set iron dial between Cotton and Linen.
- Cover design with Heat Transfer Cover Sheet or Multipurpose Paper.
- Place on flat, hard surface (ironing board not recommended).
- Press iron with medium/firm pressure for 10-15 seconds.
- Peel carrier warm.

### Application Instructions (Heat Press):

- Preheat garment for 2-3 seconds.
- Apply design at 320°F / 160°C (*EasyPress* users add approx. 30°).
- Use medium pressure for 10-15 seconds.
- Peel carrier warm.

### Laundrying:

- Wait 24 hours before first wash.
- Machine wash warm or cold with mild detergent.
- Do not bleach, dry clean, or use liquid fabric softener.
- Dry on normal dryer setting.

## Holographic

For Use On: 100% Cotton | Poly/cotton blends | 100% Polyester | Leather

*Holographic Rainbow Pearl gives your designs an opalescent finish that changes depending on the color of the garment. The material will not look the same on a black garment as it will on a white garment.*



### Application Instructions (Home Iron):

- Set iron dial between Cotton and Linen.
- Cover design with Heat Transfer Cover Sheet or Multipurpose Paper.
- Place on flat, hard surface (ironing board not recommended).
- Press iron with medium/firm pressure for 10-15 seconds.
- Peel carrier cold.

### Application Instructions (Heat Press):

- Preheat garment for 2-3 seconds.
- Apply design at 320°F / 160°C. (*EasyPress* users add approx. 30°).
- Use medium/firm pressure for 15-20 seconds.
- Peel carrier cold.

### Laundrying:

- Wait 24 hours before first wash.
- Machine wash warm or cold with mild detergent.
- Do not bleach, dry clean, or use liquid fabric softener.
- Dry on normal dryer setting.

### RECOMMENDED ACCESSORIES:

Siser® EasyWeeder®, parchment or multipurpose paper, or heat transfer cover sheet.

If areas lift after application, cover and press for 5-10 seconds.

Due to variances in the manufacturing process of fabrics, Siser highly recommends testing prior to production.



## Metal

For Use On: 100% Cotton | Poly/cotton blends | 100% Polyester



### Application Instructions (Home Iron):

- Set iron dial between Cotton and Linen.
- Cover design with Heat Transfer Cover Sheet or Multipurpose Paper.
- Place on flat, hard surface (ironing board not recommended).
- Press iron with medium/firm pressure for 10-15 seconds.
- Peel carrier cold.

### Application Instructions (Heat Press):

- Preheat garment for 2-3 seconds.
- Apply design at 305°F / 150°C (*EasyPress* users add approx. 30°).
- Use medium pressure for 10-15 seconds.
- Peel carrier cold.

### Laundering:

- Wait 24 hours before first wash.
- Machine wash cold with mild detergent.
- Do not bleach, dry clean, or use liquid fabric softener.
- Dry on low dryer setting.

## Sparkle™

For Use On: 100% Cotton | Poly/cotton blends | 100% Polyester | Leather



### Application Instructions (Home Iron):

- Set iron dial between Cotton and Linen.
- Cover design with Heat Transfer Cover Sheet or Multipurpose Paper.
- Place on flat, hard surface (ironing board not recommended).
- Press iron with medium/firm pressure for 10-15 seconds.
- Peel carrier hot or cold.

### Application Instructions (Heat Press):

- Preheat garment for 2-3 seconds.
- Apply design at 305°F / 150°C (*EasyPress* users add approx. 30°).
- Use medium/firm pressure for 15-20 seconds.
- Peel carrier hot or cold.

### Laundering:

- Wait 24 hours before first wash.
- Machine wash cold with mild detergent.
- Do not bleach, dry clean, or use liquid fabric softener.
- Dry on low dryer setting.

## StripFlock® Pro

For Use On: 100% Cotton | Poly/cotton blends | 100% Polyester | Leather



### Application Instructions (Home Iron):

- Set iron dial between Cotton and Linen.
- Cover design with Heat Transfer Cover Sheet or Multipurpose Paper.
- Place on flat, hard surface (ironing board not recommended).
- Press iron with medium/firm pressure for 10-15 seconds.
- Peel carrier warm.

### Application Instructions (Heat Press):

- Preheat garment for 2-3 seconds.
- Apply design at 311°F / 155°C (*EasyPress* users add approx. 30°).
- Use medium pressure for 10-15 seconds.
- Peel carrier warm.

### Laundering:

- Wait 24 hours before first wash.
- Machine wash warm or cold with mild detergent.
- Do not bleach, dry clean, or use liquid fabric softener.
- Dry on normal dryer setting.

## Twinkle™

For Use On: 100% Cotton | Poly/cotton blends | 100% Polyester | Leather



### Application Instructions (Home Iron):

- Set iron dial between Cotton and Linen.
- Cover design with Heat Transfer Cover Sheet or Multipurpose Paper.
- Place on flat, hard surface (ironing board not recommended).
- Press iron with medium/firm pressure for 15 seconds.
- Peel carrier warm.

### Application Instructions (Heat Press):

- Preheat garment for 2-3 seconds.
- Apply design at 305°F / 150°C (*EasyPress* users add approx. 30°).
- Use medium/firm pressure for 15 seconds.
- Peel carrier warm.

### Laundering:

- Wait 24 hours before first wash.
- Machine wash cold with mild detergent.
- Do not bleach, dry clean, or use liquid fabric softener.
- Dry on low dryer setting.

### RECOMMENDED ACCESSORIES:

Siser® EasyWeeder®, parchment or multipurpose paper, or heat transfer cover sheet.

If areas lift after application, cover and press for 5-10 seconds.

Due to variances in the manufacturing process of fabrics, Siser highly recommends testing prior to production.



Siser's latest innovation, EasyColor™ DTV (Direct to Vinyl), is a white, printable material with a matte finish designed to be compatible with desktop printer inkjet ink, Siser® EasyColor provides excellent print quality with vibrant colors. Only slightly thicker than EasyWeed®, EasyColor™ is lightweight enough for polyester applications, yet still opaque enough for light and dark fabrics. Simply print, cut, mask, and heat to make full-color creations with your desktop printer!

**Description**



White, Matte Finish, desktop printer inkjet ink compatible media

**Compatible Materials:**

Cotton, Polyester, Poly/Cotton Blends \*More fabrics to be evaluated

**Composition / Thickness:**

Film Composition: Polyurethane

Skin Thickness: Approx. 100 Microns / 3.94 Mills

Carrier Backing Composition: Polyester

Carrier Backing Thickness: Apporx. 75 Microns / 2.95 Mills

**Printer Ink Compatibility:**

Compatible with standard desktop inkjet ink. Plain paper setting for most printers. \*More ink types to be evaluated.

**Cutting**

**Roland GS-24**

- Blade: 45°
- Force: 80-90 gf
- Speed: 30-50 cm/s
- Offset: .250

**Silhouette 4**

- Blade: AutoBlade, 3
- Force: 6
- Speed: 8
- Material: Heat Transfer, Smooth

**Cricut Explore Air**

- Blade: AutoBlade
- Setting: Vinyl+

**Siser Cutter**

- Blade: 45°
- Offset: .250
- Force: 5-10
- Speed: 10

Settings may vary based on blade condition and age of machine. Always perform a test cut prior to cutting designs.

**Mask**

TTD Easy Mask

**Heat Application**

**Siser Craft Press**

- Preheat: 3 seconds
- Time: 15 seconds
- Temperature: 310°F / 155°C
- Pressure: Medium
- Peel: Hot

**Cricut EasyPress**

- Preheat: 3 seconds
- Time: 15-25 seconds
- Temperature: 340°F / 171°C
- Pressure: Medium
- Peel: Hot

**Home Iron**

- Setting: Cotton
- Time: 15-25 seconds
- Pressure: Medium
- Peel: Hot
- \* Setting and time may vary among irons

**Laundering**

- We recommend washing the garment prior to wearing to ensure that any excess ink from the printing process is removed.
- Wait 24 hours before first wash
- Machine wash cold
- Tumble dry low
- Do not bleach or dry clean

**Recommended Accessories**

- Siser EasyWeeder™
- Siser EasySqueegee™
- TTD Easy Mask